

Titre: Coiled-coil interactions: a versatile bioaffinity system for the oriented immobilization and tunable release of biomolecules from biomaterials
Title:

Auteurs: Frédéric Murschel, Charles Fortier, Robert Hodges, Mario Jolicoeur, & Gregory De Crescenzo
Authors:

Date: 2016

Type: Communication de conférence / Conference or Workshop Item


Référence: Murschel, F., Fortier, C., Hodges, R., Jolicoeur, M., & De Crescenzo, G. (mai 2016). Coiled-coil interactions: a versatile bioaffinity system for the oriented immobilization and tunable release of biomolecules from biomaterials [Affiche].
Citation: 10th World Biomaterials Congress, Montréal, Québec. Publié dans Frontiers in Bioengineering and Biotechnology, 4.
<https://doi.org/10.3389/conf.fbioe.2016.01.01520>

 **Document en libre accès dans PolyPublie**
Open Access document in PolyPublie

URL de PolyPublie: <https://publications.polymtl.ca/4870/>
PolyPublie URL:

Version: Version officielle de l'éditeur / Published version
Révisé par les pairs / Refereed

Conditions d'utilisation: CC BY
Terms of Use:

 **Document publié chez l'éditeur officiel**
Document issued by the official publisher

Nom de la conférence: 10th World Biomaterials Congress
Conference Name:

Date et lieu: 2016-05-17 - 2016-05-22, Montréal, Québec
Date and Location:

Maison d'édition: Frontiers Media S.A.
Publisher:

URL officiel: <https://doi.org/10.3389/conf.fbioe.2016.01.01520>
Official URL:

Mention légale:
Legal notice:

Coiled-coil interactions: a versatile bioaffinity system for the oriented immobilization and tunable release of biomolecules from biomaterials

Frederic Murschel^{1*}, Charles Fortier¹, Robert Hodges^{2*}, Mario Jolicoeur¹ and Gregory De Crescenzo^{1*}

¹ Ecole Polytechnique de Montréal, Department of Chemical Engineering, Canada

² University of Colorado, School of Medicine, Structural Biology and Biophysics Core Facilities, United States

Introduction: The coiled-coil assembly – a natural motif found ubiquitously in proteins – has recently (re)gained attention as a powerful tool for the development of biomaterials, in particular peptide-based and peptide-polymer hybrid nanomaterials^{[1],[2]}. We have successfully used de novo designed complementary E and K peptides for the grafting of E-tagged growth factors on various K-decorated biomaterials (**Fig. 1A**). The specific attachment of the molecules mediated by the E/K coiled-coil interactions has notably demonstrated more potency when compared to non-site specific grafting methods^[3]. This tool has been since refined, and we report here our work on the fine-tuning of the stability and affinity of the assembly by (a) precise residue substitutions in the K peptide and by (b) changes in the numbers of available E moieties on the grafted molecule.




Figure 1. Scheme of the coiled-coil interactions and the biomolecules used in this study.
A. E/K coiled-coil assembly showing hydrophobic (orange arrows) and electrostatic (black arrows) interactions.
B. Sequence of the K peptide and analogs showing 1 to 3 Leucine-to-Alanine substitutions (red).
C. Visual representation of (i) the E peptide and E-bearing biomolecules: (ii) E-tagged epidermal growth factor, (iii) E-tagged vascular endothelial growth factor and (iv) E-decorated nanoparticles.

Materials and Methods: Coil peptides and coil-tagged proteins were produced and purified as previously described^[4]. Coil-decorated nanoparticles were produced by (i) auto-assembly of branched poly(ethylene imine) (PEI) and carboxymethylated dextran (CMD) bearing vinyl sulfone (VS) reactive groups then (ii) by reacting the cysteine-terminated E peptides with the VS groups. Surface plasmon resonance (SPR)-based assays were performed at 100 $\mu\text{L}/\text{min}$ on a Biacore® T100 biosensor, using HBS-EP as running buffer.

Results and Discussion: Three K peptide analogs were designed with 1 to 3 Leucine-to-Alanine substitutions as a means to destabilize the hydrophobic core of the E/K assembly (**Fig. 1A-B**). SPR-based assays of the interaction of the E peptide with the K analogs were performed (**Fig. 2A**), and the kinetic analysis of the sensorgrams indicated that a wide range of affinities could be obtained, with apparent dissociation constants ranging from 137 pM to 14.8 nM.

Further SPR-based assays were performed with relevant biomolecules bearing a varying number of E moieties: E-tagged epidermal- and vascular endothelial growth factor, namely E-EGF and E-VEGF, as well as E-decorated PEI/CMD nanoparticles that could be used for nucleic acid encapsulation (**Fig. 1C**). The normalized responses obtained for a 50-nM injection of the tagged growth factors indicated that the number of E moieties affected both association and dissociation rates, as well as the amount that was recruited (data not shown). The enhancement of protein capture and stability was attributed to multivalent interactions occurring between the dimeric E-VEGF and the K-decorated surface, i.e., avidity causing an increase in the apparent affinity. Avidity was more plainly evidenced when nanoparticles bearing varying E densities were injected over the K peptide (**Fig. 2B**).




Figure 2. Surface plasmon resonance-based assays of coiled-coil interactions.
A. Control-corrected sensorgram of a 10-nM E peptide injection over ca. 600 RU of the K peptide and its analogs.
B. Control-corrected sensorgrams of a 50-nM injection of E-tagged EGF (yellow) and E-tagged VEGF (green) over ca. 600 RU of the K peptide (dashed lines) and the analog with 3 substitutions (solid lines).
C. Maximal response obtained after the injection of nanoparticles bearing varying E peptide surface densities over the K peptide.

Conclusion: Two levers – the sequence of the K peptide and the number of E moieties – were here identified in the use of coiled-coil interactions for the controlled grafting and release of biomolecules, be it for the direct protein attachment onto tissue engineering scaffold or the transport of drugs or nucleic acids within nanoparticles.

This work was supported by the Canada Research Chair on Protein-Enhanced Biomaterials (G.D.C.), the Canada Research Chair in Applied Metabolic Engineering (M.J.), by the Natural Sciences and Engineering Research Council of Canada (G.D.C. and M.J.), by the Fonds de recherche du Québec - Nature et technologies (F.M. and C.F.) and by the MEDITIS training program (F.M. and C.F.); We thank Josianne Lefebvre for technical support and fruitful discussion

References:

- [1] Gerling-Driessen, U. I. M.; Mujkic-Ninnemann, N.; Ponader, D.; Schöne, D.; Hartmann, L., Exploiting Oligo(amido amine) Backbones for the Multivalent Presentation of Coiled-Coil Peptides. *Biomacromolecules* 2015, 16, (8), 2394-2402.
- [2] Aronsson, C.; Dänmark, S.; Zhou, F.; Öberg, P.; Enander, K.; Su, H.; Aili, D., Self-sorting heterodimeric coiled coil peptides with defined and tuneable self-assembly properties. *Scientific Reports* 2015, 5, 14063.
- [3] Lequoy, P.; Liberelle, B.; De Crescenzo, G.; Lerouge, S., Additive benefits of chondroitin sulfate and oriented tethered epidermal growth factor for vascular smooth muscle cell survival. *Macromol. Biosci.* 2014, 14, (5), 720-30.
- [4] Murschel, F.; Liberelle, B.; St-Laurent, G.; Jolicœur, M.; Durocher, Y.; De Crescenzo, G., Coiled-coil-mediated grafting of bioactive vascular endothelial growth factor. *Acta Biomater.* 2013, 9, (6), 6806-6813.

Keywords: self-assembly, biosensing, growth factor, biofunctionalization **Conference:** 10th World Biomaterials Congress, Montréal, Canada, 17 May - 22 May, 2016.

Presentation Type: Poster **Topic:** Protein interactions with biomaterials

Citation: Murschel F, Fortier C, Hodges R, Jolicœur M and De Crescenzo G (2016). Coiled-coil interactions: a versatile bioaffinity system for the oriented immobilization and tunable release of biomolecules from biomaterials. *Front. Bioeng. Biotechnol. Conference Abstract: 10th World Biomaterials Congress*. doi: 10.3389/conf.FBIOE.2016.01.01520

Copyright: The abstracts in this collection have not been subject to any Frontiers peer review or checks, and are not endorsed by Frontiers. They are made available through the Frontiers publishing platform as a service to conference organizers and presenters.

The copyright in the individual abstracts is owned by the author of each abstract or his/her employer unless otherwise stated.

Each abstract, as well as the collection of abstracts, are published under a Creative Commons CC-BY 4.0 (attribution) licence (<https://creativecommons.org/licenses/by/4.0/>) and may thus be reproduced, translated, adapted and be the subject of derivative works provided the authors and Frontiers are attributed.

For Frontiers' terms and conditions please see <https://www.frontiersin.org/legal/terms-and-conditions>. Received: 27 Mar 2016; Published Online: 30 Mar 2016.

* Correspondence:

Dr. Frederic Murschel, Ecole Polytechnique de Montréal, Department of Chemical Engineering, Montréal, QC, Canada, Email1

Dr. Robert Hodges, University of Colorado, School of Medicine, Structural Biology and Biophysics Core Facilities, Aurora, CO, United States, robert.hodges@ucdenver.edu

Dr. Gregory De Crescenzo, Ecole Polytechnique de Montréal, Department of Chemical Engineering, Montréal, QC, Canada, gregory.decrescenzo@polymtl.ca