


Titre: Title:	Thermochromic VO2 films for smart windows application
Auteurs: Authors:	Marwan Azzi, R. Slim, K. Khoury, Simon Loquai, Bill Baloukas, & Ludvik Martinu
Date:	2018
Type:	Communication de conférence / Conference or Workshop Item
Référence: Citation:	Azzi, M., Slim, R., Khoury, K., Loquai, S., Baloukas, B., & Martinu, L. (octobre 2018). Thermochromic VO2 films for smart windows application [Communication écrite]. 5ième Congrès International Francophone de Mécanique Avancée (CIFMA 2018), Beyrouth, Lebanon (3 pages). Publié dans MATEC Web of Conferences, 261. https://doi.org/10.1051/mateconf/201926105004

 **Document en libre accès dans PolyPublie**
Open Access document in PolyPublie

URL de PolyPublie: PolyPublie URL:	https://publications.polymtl.ca/5038/
Version:	Version officielle de l'éditeur / Published version Révisé par les pairs / Refereed
Conditions d'utilisation: Terms of Use:	CC BY

 **Document publié chez l'éditeur officiel**
Document issued by the official publisher

Nom de la conférence: Conference Name:	5ième Congrès International Francophone de Mécanique Avancée (CIFMA 2018)
Date et lieu: Date and Location:	2018-10-31 - 2018-11-02, Beyrouth, Lebanon
Maison d'édition: Publisher:	EDP Sciences
URL officiel: Official URL:	https://doi.org/10.1051/mateconf/201926105004
Mention légale: Legal notice:	© The Authors, published by EDP Sciences. This is an open access article distributed under the terms of the Creative Commons Attribution License 4.0 (http://creativecommons.org/licenses/by/4.0/).

Thermochromic VO₂ films for smart windows application

M. Azzi^{1,2}, R. Slim¹, K. Khoury¹, S. Loquai², B. Baloukas², L. Martinu²

¹Lebanese University, Faculty of Engineering, Beirut Lebanon

²Ecole Polytechnique de Montréal, Montréal, Canada

Keywords: Thermochromic, VO₂, Smart windows, Energy saving

Introduction

Following the misdeeds of industrialization and consumerism of the last century, the greatest challenges of the new millennium will be to cope with global warming and energy conservation. A significant amount of energy is consumed nowadays for maintaining thermal comfort in buildings [1, 2].

Windows are known as one of the most energy inefficient components of buildings [3]. With up to 60% of the total energy loss of a building coming from its windows [4], fenestration products have a huge potential to provide large energy savings [5]. Two properties define the energetic behaviour of windows: (1) thermal transmittance, or U-value, and (2) solar factor or g-value. The first determines the heat flow across a window while the second factor determines the amount of solar energy passing through the window.

Several solutions have been proposed to improve the energy performance of windows. For the reduction of the U-value, multilayer glazing [6] and vacuum glazing [7, 8] have been developed. For the limitation of solar gain in the hot season, low emissivity (low-e) coatings [9,10] are used to let the visible light pass through and block the IR and UV wavelengths which generally create heat [11]. Because of its high IR-reflectance, this type of glazing has been substantially developed during the last two decades [12].

Vanadium dioxide VO₂ is one of the most important thermochromic materials due to a phase change that takes place at 68°C. Its practical use in smart windows for building is still facing many difficulties, mainly high transition temperature, low transmittance in the visible range and high deposition temperatures [13,14].

This work is divided into two parts; first, a building energy simulation is carried out first to estimate the energy saving potential and to determine suitable properties of smart windows for the Lebanese climate, second, deposition of VO₂ has been studied using two different deposition techniques namely the carried out using two different techniques namely the conventional Radio Frequency Magnetron Sputtering (RFMS) and the High Power Impulse Magnetron Sputtering (HiPIMS).

Results

Energy Simulation: Simulation work has shown that the use of TC windows in a typical office space in Beirut can introduce around 15% economies in the overall energy needs, including space heating, space cooling and artificial lighting. This figure was obtained when comparing TC-coated glass with clear glass. Study was based on 100 m² office building floor located on the coastal area of Lebanon simulated through EnergyPlus 8.1. However, it is necessary to underline that these encouraging results pertain to theoretical thermochromic windows, having a transition temperature of 35 °C and a switching range as wide as 5 °C, which seems to allow maximizing energy savings under all different conditions. In addition, value of daylight luminance in summer was found to be less than the minimum value, $E_{min}=300$ lx, due to the transition to tinted state.

VO₂ Deposition: Deposition results show that HiPIMS gives higher density films due high energy ions bombarding the substrate during deposition and therefore leads to better film durability. Furthermore, SiN deposited as top layer and interlayer was shown to improve significantly the durability of VO₂ layer as SiN acts as a barrier layer against humidity and improve the adhesion.

ΔT_{2500nm} parameter defined as the infrared optical modulation at 2500 nm wavelength (see schematic in Fig. 1) was used to determine the quality of the thermochromic film. It was shown that the deposition temperature T_c affects substantially ΔT_{2500nm} . For $T_c < 300^\circ C$, ΔT_{2500nm} was found to be less than 30%, however for $T_c > 300^\circ C$, values of ΔT_{2500nm} exceed 30% to reach almost 45%.




Fig. 1: Schematic graph showing the variation of the transmission spectra for a VO₂ thin film at low and high temperature phases, and definition of ΔT_{2500nm} .

Conclusions

- 1- Thermochromic VO₂ coatings have been studied for potential use in smart window applications.
- 2- Simulation work has shown that the use of TC windows with transition temperature around 35 °C in a typical office apartment in Beirut can introduce around 15% economies in the overall energy needs in office.
- 3- VO₂ layer deposited by HiPIMS was shown to have higher density due high energy ions bombarding the substrate/layer during deposition and therefore leads to better film durability.
- 4- SiN deposited as top layer and interlayer was shown to improve significantly the durability of VO₂ layer.

References

- [1] M. Kamalisarvestani, R. Saidur, S. Mekhilef, F.S. Javadi, *Performance, Renewable and Sustainable Energy Reviews* 26 (2013) 353–364.
- [2] Department of Energy U. Buildings energy data book. Energy Efficiency & Renewable Energy. 2011.
- [3] Baetens R, Jelle BP, Gustavsen *Solar Energy Materials and Solar Cells*. 2010; 94 (2):87–105.
- [4] A.Gustavsen, B.P.Jelle, D.Arasteh, C.Kohler, Project Report 6, SINTEF Building and Infrastructure, 2007.
- [5] B. P. Jelle, A. Hynd, A. Gustavsen, D. Arasteh, H. Goudey, R. Hart, *Solar Energy Materials and Solar Cells* 96 (2012) 1 – 28.
- [6] H. Manz, *Renewable Energy* 33 (2008) 119–128.
- [7] P.C. Eames, *Vacuum* 82 (2008) 717–722.
- [8] Y. Fang, T. Hyde, N. Hewitt, P.C. Eames, B. Norton, *Solar Energy Materials and Solar Cells* 93 (2009) 1492–1498.
- [9] K. Chiba, T. Takahashi, T. Kageyama, H. Oda, Low-emissivity coating of amorphous diamond-like carbon/Ag-alloy multilayer on glass, *Applied Surface Science* 246 (2005) 48–51.
- [10] M. Reidinger, M. Rydzek, C. Scherdel, M. Arduini-Schuster, J. Manara, *Thin Solid Films* 517 (2009) 3096–3099.
- [11] Sadineni SB, Madala S, Boehm RF. *Renewable and Sustainable Energy Reviews* 2011; 15 (8): 3617–31.
- [12] Huang S, et al. *Thin Solid Films* 2008; 516 (10): 3179–83.
- [13] Kivaisi R, Samiji M. *Solar Energy Materials and Solar Cells* 1999; 57 (2): 141–52.
- [14] Li S-Y, Niklasson GA, Granqvist CG. *Thermochromism MRS proceedings*. Cambridge Univ Press;2011.